

# Carbon Fiber

*Fabrics / Clothes*



## Specifications

Product Identification	Construction	Carbon Type		Density (count/cm)		Thickness (mm)	Weight (g/m2)	Width (cm)
		warp	fill	warp	fill			
CF 1115	Plain	1 K	1 K	8.8	8.8	0.15	120	102
CG 150P-T	Plain/2x2twill	1 K	1 K	12	10	0.145	150	100
CG 200P	Plain	3 K	3 K	4.8	4.8	0.20	200	100
CF 3327	Plain	3 K	3 K	5.1	5.1	0.27	208	102
CF6638	Plain	6 K	6 K	4.1	4.1	0.38	337	102
CG 370P	Plain	12 K	12 K	2.3	2.3	0.36	370	100
CG 400P	Plain	12 K	12 K	2.5	2.5	0.38	400	100

## Packaging

Each roll is wrapped in a PE-film bag.

## Storage

Our Carbon fiber fabrics/clothes should be stored in its original packaging.

Temperature should not exceed 35 degrees C and the relative humidity should be kept below 70 %.

---

FRP Services reserves the right to change the information given herein without prior notice. We believe this information to be reliable, but do not guarantee its applicability to the user's process or assume liability for occurrence arising out of its use. The user, by accepting products described herein agrees to be responsible for thoroughly testing any application before committing to production.



### FRP SERVICES & COMPANY

1-15-9 Awaza, Nishi-ku, Osaka 550-0011, Japan

TEL:+81-6-6535-1933 FAX:+81-6-6535-1675

[www.frp-services.com](http://www.frp-services.com)